



Fire Resistance Test Results

ABSTRACT

Test Specimen: Lumberock 5/4, 2x6, 1 formulation

Test Standard: ASTM E84-05

Test Date: September 1, 2006

Test Sponsor: EPS Plastic Lumber

Test Results:

FLAME SPREAD INDEX = 60

SMOKE DEVELOPED INDEX = 1100

= N/A ft Beyond Burners Centerline


Eric G. Hutchinson
Project Manager
Reviewed and approved:

September 5, 2006


C. Anthony Peñalosa
Flammability Testing Team Leader

September 5, 2006